



Durum Stucco

TDS

COD. 303/....

Solvent-based alkyd resin filler for exteriors and interiors.

Suitable for low and medium thickness applications.

Excellent adhesion properties and easy to sand when dry or damp.

Suitable for wood and iron substrates.

TYPICAL CHEMICAL AND PHYSICAL CHARACTERISTICS

APPEARANCE	matt	
COMPOSITION	alkyd resin binder	
SPECIFIC WEIGHT	1.71 ± 0.02 g/cm ³ at 20°C	
BROOKFIELD VISCOSITY	240,000 ± 40,000 cP	G7 V10 at 20°C
DRY RESIDUE	82.0 ± 0.5 % p/p	

For reference standards, see “Key – technical data sheets”

TYPICAL APPLICATION CHARACTERISTICS

DRYING (at 20°C and 65% R.H.)	can be sanded when wet after 15-24 hours; thin coats can be applied at intervals of 30-40 minutes
EFFECTIVE COVERAGE	variable depending on the thickness applied
DILUTION (V/V)	ready to use; if necessary, up to 1% Diluente 700
TOOLS	spalter

COLOURS

White,





Durum Stucco

TDS

COD. 303/....

APPLICATION SYSTEM

SUBSTRATES: wood, iron.

SUBSTRATE PREPARATION: substrates must be sound, dry, clean, firm and without traces of dirt, grease, etc.

Fully remove flaking or chalky old paintwork by careful brushing, sanding or chemical stripping; old paintwork that is still in good condition must be cleaned, degreased and sanded or brushed.

TECHNICAL SPECIFICATIONS (for contracts and quotations)

GENERAL CHARACTERISTICS	solvent-based alkyd resin filler for exteriors and interiors
DRY RESIDUE	82.0 ± 0.5 % p/p
PESO SPECIFICO	1.71 ± 0.02 g/cm ³ at 20°C

GENERAL INFORMATION AND NOTICES

The filler requires suitable re-coating, particularly for outdoor applications.

Store the product in a cool place. Do not allow to freeze.

The technical information provided above is the result of careful laboratory testing and practical experience. Nevertheless, as the product is often used outside our control, we are unable to guarantee the quality of the end result. This information is subject to review by the Company.

Please carefully read the "GENERAL RECOMMENDATIONS".

CQ Rev. 2 - May 2006

"In accordance with European Directive 2004/42/EC, the VOC values displayed on the packaging refer to the dilutions and thinners specified and to tinted products based on the formulations indicated by Boero Bartolomeo SpA."