



# Satinello

## TDS

COD. 104/....

Satin alkyd-gelled anti-rust enamel with eggshell effect.

Stands out for ease of application; does not drip or run.

Odourless application, good flow and premium aesthetic appearance.

Particularly suitable for interior substrates, such as doors, furniture, windows, etc.

### TYPICAL CHEMICAL AND PHYSICAL CHARACTERISTICS

APPEARANCE	matt-satin	
COMPOSITION	alkyd-gelled resin binder	
SPECIFIC WEIGHT	1.30 ± 0.02 g/cm <sup>3</sup> at 20°C	
BROOKFIELD VISCOSITY	7,000 ± 1,000 cP	G3 V10 at 20°C
DRY RESIDUE	67.0 ± 0.5% p/p	
GLOSS	24 ± 4 units at 60°	

For reference standards, see “Key – technical data sheets”

### TYPICAL APPLICATION CHARACTERISTICS

DRYING (at 20°C and 65% R.H.)	dust free: 25 minutes for re-coating: 24 hours complete: > 48 hours
EFFECTIVE COVERAGE	10-11 m <sup>2</sup> /L per coat depending on substrate absorption
DILUTION (V/V)	brush/roller application: 5% Diluente 900 spray application: 10% Diluente 703
TOOLS	brush, roller, spray

### COLOURS

White,





### APPLICATION SYSTEM

**SUBSTRATES:** wood, iron with no flaking calamine and rust.

**SUBSTRATE PREPARATION:** substrates must be sound, dry, clean firm and without traces of dirt, grease, etc.

Fully remove flaking or chalky old paintwork by careful brushing, sanding or chemical stripping; old paintwork that is still in good condition must be cleaned, degreased and sanded or brushed.

	NEW IRON		NEW WOOD		PAINTED SUBSTRATES (well-anchored paint)	
PRIMER	BIOFER	1 COAT	BIOFER	1 COAT	-	
FINISH	SATINELLO	2 COATS	SATINELLO	2 COATS	SATINELLO	2 COATS

If the primer has been applied for more than 72 hours, sand lightly before applying the finish.

### TECHNICAL SPECIFICATIONS (for contracts and quotations)

GENERAL CHARACTERISTICS	satin alkyd-gelled anti-rust enamel with alkyd-gelled resins
DRY RESIDUE	67.0 ± 0.5% p/p
SPECIFIC WEIGHT	1.30 ± 0.02 g/cm <sup>3</sup> at 20°C

### GENERAL INFORMATION AND NOTICES

Store the product in a cool place. Do not allow to freeze.

*The technical information provided above is the result of careful laboratory testing and practical experience. Nevertheless, as the product is often used outside our control, we are unable to guarantee the quality of the end result. This information is subject to review by the Company.*

*Please carefully read the "GENERAL RECOMMENDATIONS".*

**CQ Rev. 4 - September 2010**

***"In accordance with European Directive 2004/42/EC, the VOC values displayed on the packaging refer to the dilutions and thinners specified and to tinted products based on the formulations indicated by Boero Bartolomeo SpA."***