



Transparent wood stain with wax-like finish for interiors and exteriors.

Ideal for decorating and protecting woodwork (doors, windows, furniture, DIY items, etc.), even when exposed to mountain and marine environments.

Contains natural waxes that penetrate deep into the wood without clogging the pores, rendering the treated surface water-repellent and also microporous.

Highly resistant to the aggressive action of the sun and atmospheric agents, this product is easy to apply and doesn't peel.

The satin wax-like finish delicately transforms the appearance of wood without hiding its natural grain, making it pleasing to the touch and altering the colour to the desired shade. Brings out the best in even lower quality wood.

TYPICAL CHEMICAL AND PHYSICAL CHARACTERISTICS

APPEARANCE	satin/wax-like	
COMPOSITION	modified acrylic resin binder and special waxes	
SPECIFIC WEIGHT	0.92 ± 0.03 g/cm ³ at 20°C	
VISCOSITY	25 ± 5s	DIN 4 cup at 20°C
DRY RESIDUE	37.7 ± 0.5% p/p	

For reference standards, see “Key – technical data sheets”

COLOURS

White,





TYPICAL APPLICATION CHARACTERISTICS

DRYING (at 20°C and 65% R.H.)	for re-coating: 24 hours due to the presence of special waxes, complete drying requires several days*
EFFECTIVE COVERAGE	8-10 m²/L for 1st coat; 18-19 m²/L for subsequent coats depending on wood absorption
DILUTION (V/V)	ready for use
TOOLS	brush

* Low temperatures and/or high humidity during application may increase drying time.

APPLICATION SYSTEM

SUBSTRATES: timber

SUBSTRATE PREPARATION: substrates must be in good condition, dry and without traces of dirt, grease, resin, etc. Before starting the cycle, it is essential to sand the substrate using fine grit sandpaper. On resinous wood, we advise pre-treatment with nitro thinner. Fully remove old paintwork (enamels, varnishes, etc.) by sanding or chemical stripping. If the wood is already treated with wood stain, like Biolegno, de-dusting and de-greasing the substrates is sufficient.

	NEW WOOD		WOOD TREATED WITH WOOD STAIN		STRIPPED WOOD	
PRIMER	BIOLEGNO NEUTRO	1 COAT	-		BIOLEGNO NEUTRO	1 COAT
FINISH	BIOSETA	2-3 COATS	BIOSETA	2-3 COATS	BIOSETA	2-3 COATS

TECHNICAL SPECIFICATIONS (for contracts and quotations)

GENERAL CHARACTERISTICS	protective wood stain with modified alkyd resins and special waxes, for exteriors and interiors
DRY RESIDUE	37.7 ± 0.5% p/p
SPECIFIC WEIGHT	0.92 ± 0.03 g/cm³ at 20°C



Bioseta

TDS

COD. 135/....

GENERAL INFORMATION AND NOTICES

Mix carefully before use. Apply in well-ventilated areas. To avoid defects in formation film, do not apply in direct sunlight and windy conditions or at temperatures below 5°C.

Wood exposed to outdoor environments must not be treated with Bioseta

Neutro only.

The tints in this collection are influenced by the colour of the wood substrate and the application method; we advise prior testing.

Store the product at a temperature above 5°C.

The technical information provided above is the result of careful laboratory testing and practical experience. Nevertheless, as the product is often used outside our control, we are unable to guarantee the quality of the end result. This information is subject to review by the Company.

Please carefully read the "GENERAL RECOMMENDATIONS".

CQ Rev. 4 – April 2015

"In accordance with European Directive 2004/42/EC, the VOC values displayed on the packaging refer to the dilutions and thinners specified and to tinted products based on the formulations indicated by Boero Bartolomeo SpA."